



Armand Products Company
469 North Harrison Street • Princeton, NJ 08543-5297
Phone (800) 522-0540 • Fax (800) 335-8861

Technical Service
Phone (716) 278-7071 • Fax (716) 278-7297

Potassium Carbonate Glass, Anhydrous

SALES SPECIFICATION

Component	Basis	Specification ¹
Total Alkalinity (as K ₂ CO ₃)	wt. %	99.5 Min.
KOH	wt. %	0.20 Max.
KCl	wt. %	0.01 Max.
H ₂ O	wt. %	0.5 Max.
Na	wt. %	0.38 Max.
K ₂ SO ₄	ppm by wt.	75 Max.
As	ppm by wt.	3.0 Max.
Fe	ppm by wt.	2.0 Max.
Heavy Metals (as Pb)	ppm by wt.	5.0 Max.
Hg	ppm by wt.	0.05 Max.
Ni	ppm by wt.	1.0 Max.
Pb	ppm by wt.	2.0 Max.

Particle Size Distribution (not a specification item)

Typical Range

- 26 mesh to + 80 mesh

Notes:

¹Meets Food Chemical Codex (FCC) and The United States Pharmacopeia/The National Formulary (USP/NF) specifications.

Rev. 11/09

All information, recommendations and suggestions appearing in this bulletin concerning the use of our products are based upon tests and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee, expressed or implied, is made by Armand Products Company as to the effects of such use or results to be obtained, nor does Armand Products Company assume any liability arising out of use by others of the products referred to herein. Nor is the information herein to be construed as absolutely complete since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws of government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.