



Armand Products Company  
469 North Harrison Street • Princeton, NJ 08543-5297  
Phone (800) 522-0540 • Fax (800) 335-8861

Technical Service  
Phone (716) 278-7071 • Fax (716) 278-7297

## POTASSIUM BICARBONATE TECHNICAL GRADE

# SALES SPECIFICATION

Component	Basis	Specification
Total Alkalinity (as $\text{KHCO}_3$ , dry basis)	wt. %	97.5 Min.
Loss on Drying	wt. %	0.5 Max.
Flow Agent (MgO)	wt. %	0.99 Max.
Heavy Metals (as Pb)	ppm by wt.	10.0 Max.

Following items are not part of guaranteed specifications.

**Bulk Density** 68 lb./cu. ft.

**Particle Size Distribution** (typical values)

Sieve Size	Cumulative % retained
20	< 1.0
80	50
100	70
200	95

Rev. 08/03

All information, recommendations and suggestions appearing in this bulletin concerning the use of our products are based upon tests and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee, expressed or implied, is made by Armand Products Company as to the effects of such use or results to be obtained, nor does Armand Products Company assume any liability arising out of use by others of the products referred to herein. Nor is the information herein to be construed as absolutely complete since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws of government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.