



Armand Products Company
500 Charles Ewing Boulevard, Ewing, NJ 08628
Phone: 609 806 1602 Fax: 609 403 7280

Technical Service
Phone: 800 733 1165 Option 2

Potassium Carbonate Glass, Anhydrous

SALES SPECIFICATION

Component	Basis	Specification	
Total Alkalinity (as K ₂ CO ₃)	wt. %	99.5	Min.
KOH	wt. %	0.20	Max.
KCl	wt. %	0.01	Max.
H ₂ O	wt. %	0.5	Max.
Na	wt. %	0.38	Max.
K ₂ SO ₄	ppm by wt.	75	Max.
As	ppm by wt.	3.0	Max.
Fe	ppm by wt.	2.0	Max.
Heavy Metals (as Pb)	ppm by wt.	5.0	Max.
Hg	ppm by wt.	0.05	Max.
Ni	ppm by wt.	1.0	Max.
Pb	ppm by wt.	2.0	Max.

Notes:

- Typical Particle Size Distribution (PSD) Range: -26 mesh to +80 mesh. PSD is not a specification item and is provided for informational purposes only.
- Meets Food Chemicals Codex (FCC) chemical test requirements.
- Potassium Carbonate is not produced under all cGMP requirements as defined by the FDA.

IMPORTANT: The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE, OR WARRANTY OR GUARANTY OF ANY OTHER KIND, EXPRESS OR IMPLIED, IS MADE REGARDING PERFORMANCE, SAFETY, SUITABILITY, STABILITY OR OTHERWISE. This information is not intended to be all-inclusive as to the manner and conditions of use, handling, storage, disposal and other factors that may involve other or additional legal, environmental, safety or performance considerations, and Armand Products assumes no liability whatsoever for the use of or reliance upon this information. While our technical personnel will be happy to respond to questions, safe handling and use of the product remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patents or to violate any Federal, State, local or foreign laws.